



Excellence Beyond Expectation

➤ **Product Name: Chloroprene**

Technical Parameters

Product	Baypren® 110
Crystallization	very low
Mooney Viscosity ML(1+4) 100 °C	49 +/-5
Density(g/cm³)	1.23
Physical form	ivory-colored chip
Packaging	25 kg paper bags with PE inner bags (0.05 mm thick, Vicat softening point DIN 53 460, ca. 75°C); 40 bags pallet = 1.000 kg net /35 bags pallet = 875 kg net. Also available only on request: 20 kg PE bags; 50 bags per pallet = 1.000 kg net / 40 bags per pallet = 800 kg net / 25 kg PE bags 40 bags per pallet = 1000 kg ne

Applications:

Automotive
Industry
Energy
Construction
Polymer auxiliaries
Textile industry
Sports and leisure
Plastic- and Rubber polymers
Machine and equipment construction